



**Product Data Sheet &
General Processing Conditions**

**RTP 2287 HF UP
Polyetheretherketone (PEEK)
Carbon Fiber
High Flow
Ultra Performance**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

| PERMANENCE | | STANDARD |
|-------------------|------------------------|-----------------|
| Primary Additive | 40 % | |
| Density | 1.45 g/cm ³ | ISO 1183 |

| MECHANICAL | | |
|---------------------------|----------------------|------------|
| Impact Strength, Izod | | |
| Notched, 4 mm thickness | 7 kJ/m ² | ISO 180/1A |
| Unnotched, 4 mm thickness | 55 kJ/m ² | ISO 180/1U |
| Tensile Strength | 305 MPa | ISO 527 |
| Tensile Elongation | 1.3 % | ISO 527 |
| Tensile Modulus | 4000 MPa | ISO 527 |
| Flexural Strength | 470 MPa | ISO 178 |
| Flexural Modulus | 33800 MPa | ISO 178 |

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.
Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

GENERAL PROCESSING FOR INJECTION MOLDING

| | |
|--------------------|----------------|
| Injection Pressure | 80 - 125 MPa |
| Injection Pressure | 820 - 1240 bar |
| Melt Temperature | 350 - 400 °C |
| Mold Temperature | 160 - 220 °C |
| Drying | 3 hrs @ 150 °C |
| Moisture Content | 0.10 % |
| Dew Point | -30 °C |

PROCESSING NOTES

Desiccant Type Dryer Required.

21 Dec 2018 BJJ

This information is intended to be used only as a guideline for designers and processors of modified thermoplastics. Because design and processing is complex, a set solution will not solve all problems. Observation on a "trial and error" basis may be required to achieve desired results.

Data are obtained from specimens molded under carefully controlled conditions from representative samples of the compound described herein. Properties may be materially affected by molding techniques applied and by the size and shape of the item molded. No assurance can be implied that all molded articles will have the same properties as those listed.

No information supplied by RTP Company constitutes a warranty regarding product performance or use. Any information regarding performance or use is only offered as suggestion for investigation for use, based upon RTP Company or other customer experience. RTP Company makes no warranties, expressed or implied, concerning the suitability or fitness of any of its products for any particular purpose. It is the responsibility of the customer to determine that the product is safe, lawful and technically suitable for the intended use. The disclosure of information herein is not a license to operate

under, or a recommendation to infringe any patents.

RTP COMPANY • 580 EAST FRONT STREET • WINONA, MN 55987 • 507-454-6900