



Processing Conditions

Polyetherketoneketone (PEKK) — RTP 4100 Series Specialty Compounds

Typical Injection Molding Conditions

	English	SI Metric
Temperatures		
Rear zone	680 - 705 °F	360 - 374 °C
Center zone	690 - 710 °F	366 - 377 °C
Front zone	700 - 720 °F	371 - 382 °C
Melt	710 - 720 °F	377 - 382 °C
Mold	425 - 450 °F	218 - 232 °C

Pressures		
Injection	15000 - 20000 psi	103 - 138 MPa
Hold	10000 - 15000 psi	69 - 103 MPa
Back	50 - 100 psi	0.34 - 0.69 MPa

Speeds		
Fill	2 - 3 in/sec	51 - 76 mm/sec
Screw	60 - 90 rpm	60 - 90 rpm

Drying		
Time & Temperature	3 Hrs @ 300 °F	3 Hrs @ 149 °C
Dew Point	-20 °F	-29 °C
Moisture Content	0.10 %	0.10 %

Notes

- This information is intended to be used only as a guideline for designers and processors of modified thermoplastics for injection molding. Because injection mold design and processing is complex, a set solution will not solve all problems. Observation on a "trial and error" basis may be required to achieve desired results.
- No information supplied by RTP Company constitutes a warranty regarding product performance or use. Any information regarding performance or use is only offered as suggestion for investigation for use, based upon RTP Company or other customer experience. RTP Company makes no warranties, expressed or implied, concerning the suitability or fitness of any of its products for any particular purpose. It is the responsibility of the customer to determine that the product is safe, lawful and technically suitable for the intended use. The disclosure of information herein is not a license to operate under, or a recommendation to infringe any patents.