



**Product Data Sheet &
General Processing Conditions**

**RTP 2800 B-75A FR A
Thermoplastic Vulcanizate (TPV)
Flame Retardant
PBDE Free**



PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Specific Gravity	1.25	1.25	D 792
MECHANICAL			
Tensile Strength Die C, 0.125 in, 20 in/min (3.2mm, 500 mm/min)	750 psi	5 MPa	D 412
Tensile Elongation Break, Die C, 0.125 in, 20 in/min (3.2mm, 500 mm/min)	500.0 %	500.0 %	D 412
Tensile Stress Die C 0.125 in, 20 in/min (3.2 mm, 500 mm/min) @ 100 %	420.0 psi	2.9 MPa	D 412
Tear Strength, Die C	155.0 pli	27.2 N/mm	D 624
Compression Set 22 h @ 23 °C (73 °F), Method B, Type 2	30 %	30 %	D 395
22 h @ 70 °C (158 °F), Method B, Type 2	48 %	48 %	D 395
Hardness Shore A, 10 s delay	75	75	D 2240

ELECTRICAL

Dielectric Strength, S/T, in oil	451 VPM	17.8 kV/mm	D 149
Dielectric Constant, 1 MHz, Dry	< 2.5	< 2.5	D 150
Dissipation Factor, 1 MHz, Dry	< 0.0040	< 0.0040	D 150

THERMAL

Ignition Resistance* Flammability	V-0 @ 1/16 in	V-0 @ 1.5 mm	UL94
--------------------------------------	---------------	--------------	------

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	12000 - 18000 psi	83 - 124 MPa
Melt Temperature	360 - 410 °F	182 - 210 °C
Mold Temperature	60 - 150 °F	16 - 66 °C
Drying	2 hrs @ 175 °F	2 hrs @ 79 °C
Moisture Content	0.03 %	0.03 %
Dew Point	0 °F	-18 °C

PROCESSING NOTES

This information is intended to be used only as a guideline for designers and processors of modified thermoplastics. Because design and processing is complex, a set solution will not solve all problems. Observation on a "trial and error" basis may be required to achieve desired results.

Data are obtained from specimens molded under carefully controlled conditions from representative samples of the compound described herein. Properties may be materially affected by molding techniques applied and by the size and shape of the item molded. No assurance can be implied that all molded articles will have the same properties as those listed.

No information supplied by RTP Company constitutes a warranty regarding product performance or use. Any information regarding performance or use is only offered as suggestion for investigation for use, based upon RTP Company or other customer experience. RTP Company makes no warranties, expressed or implied, concerning the suitability or fitness of any of its products for any particular purpose. It is the responsibility of the customer to determine that the product is safe, lawful and technically suitable for the intended use. The disclosure of information herein is not a license to operate under, or a recommendation to infringe any patents.

RTP COMPANY • 580 EAST FRONT STREET • WINONA, MN 55987 • 507-454-6900